



# FIRE-RATED, SAFETY-RATED GLASS CERAMIC

FireLite Plus® Forced Entry is a laminated, fire-rated, 3/8" (10 mm) glass. Tested in accordance with H.P. White 5-aa1 and ASTM E2395.





#### **FEATURES**

- ultraHD® Technology for improved surface quality, clarity and color
- Fire-rated for up to 180 minutes in the same large sizes as FireLite Plus
- Clear and wireless glass ceramic
- Impact safety-rated-meets ANSI Z97.1 and CPSC 16 CFR1201 (Cat. I and II)
- May be lightly sandblasted or etched by others on one side without affecting fire rating

- Protects from fire and impact on both sides of the glass
- 5-year limited warranty
- Tested and certified to ASTM E2395 when used as an IGU in TGProtect™ FR System
- · Can be used in doors by others
- · Withstands thermal shock



BIM 3D Model



Fire-Rated



Hose Stream Tested



Positive Pressure Tested



Impacted Rated



Forced Entry Resistant



**UL Classified & Labeled** 



NORTH AMERICA'S MOST SPECIFIED FIRE-RATED GLASS COMPANY

NOTE: This product is not a barrier to radiant heat, as it does not meet test standards ASTM E119 or UL 263. If your jurisdiction requires a barrier to heat product, please contact TGP regarding Pilkington Pyrostop®.

### LISTINGS/STANDARDS

Classified and labeled by Underwriters Laboratories, Inc.® and Underwriters Laboratories of Canada. File number for labeled fire-rated assemblies is R13377. Tests performed in accordance with:

UL 9 NFPA 80 CAN/ULC-S104 MEA-290-90-M-6
UL 10C NFPA 257 CAN/ULC-S106 LARR 25798









# **MAXIMUM EXPOSED AREA**

RATING	ASSEMBLY	MAX. EXPOSED AREA	MAX. WIDTH OF EXPOSED GLAZING	MAX. HEIGHT OF EXPOSED GLAZING R
20 to 60 min.	DOORS (non-temp rise) DOORS (temp rise) OTHER THAN DOORS	3,204 in <sup>2</sup> / 22.25 ft <sup>2</sup> (2.07 m <sup>2</sup> ) 100 in <sup>2</sup> / 0.69 ft <sup>2</sup> (.06 m <sup>2</sup> ) 3,325 in <sup>2</sup> / 23.09 ft <sup>2</sup> (2.15 m <sup>2</sup> )	36" (914 mm) 12" (304 mm) 95" (2,413 mm)	89" (2,260 mm) 33" (838 mm) 95" (2,413 mm)
90 min.	DOORS (non-temp rise) DOORS (temp rise) OTHER THAN DOORS	2,034 in <sup>2</sup> / 14.13 ft <sup>2</sup> (1.31 m <sup>2</sup> ) 100 in <sup>2</sup> / 0.69 ft <sup>2</sup> (.06 m <sup>2</sup> ) 2,627 in <sup>2</sup> / 18.24 ft <sup>2</sup> (1.69 m <sup>2</sup> )	36" (914 mm) 12" (304 mm) 56-1/2" (1,435 mm)	56-1/2" (1,435 mm) 33" (838 mm) 56-1/2" (1,435 mm)
180 min.	DOORS	100 in <sup>2</sup> / 0.69 ft <sup>2</sup> (.06 m <sup>2</sup> )	12" (304 mm)	33" (838 mm)

Check with frame manufacturer for maximum tested glass sizes and required stop height.

Note: Individual lite sizes cannot exceed "Max. Exposed Area" shown above.

#### **MAXIMUM SHEET SIZE**

48" x 96" (1.21 m x 2.43 m)

#### **GENERAL CHARACTERISTICS**

THICKNESS: Nominal 3/8"(10 mm nominal) overall

**WEIGHT:**  $4.5 \text{ lb} / \text{ft}^2 (21.97 \text{ kg} / \text{m}^2)$ 

APPROX. VISIBLE TRANSMISSION: 85%
APPROX. VISIBLE REFLECTION: 9%
HARDNESS (VICKER'S SCALE): 700

FIRE RATING: 20 - 180 minutes

IMPACT SAFETY RATING: Meets ANSI Z97.1 and CPSC 16CFR1201 (Cat. I and II)

STC RATING: 38

## **LABELING**

Each piece of FireLite Plus Forced Entry shall be permanently labeled with the FireLite Plus Forced Entry logo, UL logo and fire rating.

# **STORAGE & HANDLING**

FireLite Plus Forced Entry must be handled with care during transportation, storage, inspection and installation. Store in a dry place.



